


What is claimed is:

1. A flame retardant thermoplastic resin composition comprising:

(A) 100 parts by weight of a thermoplastic resin as a base resin;

(B) about 0.1~100 parts by weight of a phenol resin derivative represented by

5 the following Formula;



10 where R_1 is alkyl of C_{1-34} ; aryl; alkyl-substituted aryl; O-, N-, P- or S-containing alkyl; O-, N-, P- or S-containing aryl; or O-, N-, P- or S-containing alkyl-substituted aryl; R_2 , R_3 , and R_4 are hydrogen, alkyl of C_{1-34} ; aryl; alkyl-substituted aryl; O-, N-, P- or S-containing alkyl; O-, N-, P- or S-containing aryl; or O-, N-, P- or S-containing alkyl-substituted aryl; and n is an integer of 1 to 10,000; and


15

(C) about 1~50 parts by weight of a phosphoric acid ester morpholide compound.

2. The flame retardant thermoplastic resin composition as defined in claim 1, wherein said base resin is selected from the group consisting of polyacrylonitrile-butadiene-styrene copolymer (ABS resin), rubber modified polystyrene resin (HIPS), acrylonitrile-styrene-acrylate copolymer (ASA resin), methacrylate-butadiene-styrene copolymer (MBS resin), acrylonitrile-ethacrylate-styrene copolymer (AES resin), polycarbonate (PC), polyethylene (PE), polypropylene (PP), polyethylene terephthalate (PET), polybutylene terephthalate (PBT), polyvinyl chloride (PVC), polymethyl methacrylate (PMMA), polyamide (PA), and a
20 copolymer thereof and an alloy thereof.
25

3. The flame retardant thermoplastic resin composition as defined in claim 1, wherein said phenol resin derivative is selected from the group consisting of o-cresol novolak epoxy resin, phenol epoxy resin and a mixture thereof.

5 4. The flame retardant thermoplastic resin composition as defined in claim 1, wherein said phosphoric acid ester morpholide compound is represented by the following Formula:



10 where R_1 is a C_{6-20} aryl group or an alkyl-substituted C_{6-20} aryl group, R_2 is a C_{6-30} aryl group or an alkyl-substituted C_{6-30} aryl group, x is 1 or 2, and n and m are number average degree of polymerization and $n+m$ is 0 to 5.

5 15 5. The flame retardant thermoplastic resin composition as defined in claim 1, where R_1 is phenyl group or an alkyl-substituted phenyl group, where the alkyl is methyl, ethyl, isopropyl, t-butyl, isoamyl or t-amyl and R_2 is a C_{6-30} aryl group or an alkyl-substituted C_{6-30} aryl group which is a derivative from resorcinol, hydroquinone, or bisphenol-A.

20 6. The flame retardant thermoplastic resin composition as defined in claim 1, further comprising an additive selected from the group consisting of an impact modifier, a heat stabilizer, an oxidation inhibitor, a light stabilizer, and an inorganic filler such as talc, silica, mica, glass fiber, an organic or inorganic pigment and/or dye up to about 50 parts by weight as per 100 parts by weight of the base resin.

7. A molded article prepared by the flame retardant thermoplastic resin composition of claim 1.


8. A molded article prepared by the flame retardant thermoplastic resin composition of claim 4.

9. A flame retardant thermoplastic resin composition comprising:

(A) 100 parts by weight of a thermoplastic resin as a base resin;

(B) about 0.1~100 parts by weight of polyphenylene ether;

(C) about 0.1~100 parts by weight of a phenol resin derivative represented by the following Formula (I);



where R_1 is alkyl of C_{1-34} ; aryl; alkyl-substituted aryl; O-, N-, P- or S-containing alkyl; O-, N-, P- or S-containing aryl; or O-, N-, P- or S-containing alkyl-substituted aryl; R_2 , R_3 , and R_4 are hydrogen, alkyl of C_{1-34} ; aryl; alkyl-substituted aryl; O-, N-, P- or S-containing alkyl; O-, N-, P- or S-containing aryl; or O-, N-, P- or S-containing alkyl-substituted aryl; and n is an integer of 1 to 10,000; and

(D) about 0.1~50 parts by weight of a phosphoric acid ester morpholide compound.


10. The flame retardant thermoplastic resin composition as defined in claim 9, further comprising up to about 5.0 parts by weight of an anti-dripping agent based on 100 parts by weight of the base resin.

5 11. The flame retardant thermoplastic resin composition as defined in claim 10, wherein said anti-dripping agent is a fluoride resin.

12. The flame retardant thermoplastic resin composition as defined in claim 9, wherein said base resin is selected from the group consisting of polyacrylonitrile-
10 butadiene-styrene copolymer (ABS resin), rubber modified polystyrene resin (HIPS), acrylonitrile-styrene-acrylate copolymer (ASA resin), methacrylate-butadiene-styrene copolymer (MBS resin), acrylonitrile-ethacrylate-styrene copolymer (AES resin), polycarbonate (PC), polyethylene (PE), polypropylene (PP), polyethylene terephthalate (PET), polybutylene terephthalate (PBT), polyvinyl chloride (PVC), polymethyl
15 methacrylate (PMMA), polyamide (PA), and a copolymer thereof and an alloy thereof.

13. The flame retardant thermoplastic resin composition as defined in claim 9, wherein said phenol resin derivative is selected from the group consisting of o-cresol novolak epoxy resin, phenol epoxy resin and a mixture thereof.

20 14. The flame retardant thermoplastic resin composition as defined in claim 9, wherein said phosphoric acid ester morpholide compound is represented by the following Formula (V):



where R_1 is a C_{6-20} aryl group or an alkyl-substituted C_{6-20} aryl group, R_2 is a C_{6-30} aryl group or an alkyl-substituted C_{6-30} aryl group, x is 1 or 2, and n and m are number average degree of polymerization and $n+m$ is 0 to 5.

15. The flame retardant thermoplastic resin composition as defined in claim 14, where R_1 is phenyl group or an alkyl-substituted phenyl group, where the alkyl is methyl, ethyl, isopropyl, t-butyl, isoamyl or t-amyl and R_2 is a C_{6-30} aryl group or an alkyl-substituted C_{6-30} aryl group which is a derivative from resorcinol, hydroquinone, or bisphenol-A.

16. The flame retardant thermoplastic resin composition as defined in claim 10, further comprising an additive selected from the group consisting of an impact modifier, a heat stabilizer, an oxidation inhibitor, a light stabilizer, and an inorganic filler such as talc, silica, mica, glass fiber, an organic or inorganic pigment and/or dye up to about 50 parts by weight as per 100 parts by weight of the base resin.

17. A molded article prepared by the flame retardant thermoplastic resin composition of claim 9.

18. A molded article prepared by the flame retardant thermoplastic resin composition of claim 14.